



RUST-OLEUM® CEMENT FINISH

DESCRIPTION AND USES

Rust-Oleum® Cement Finish is a faux finish that provides the natural look and feel of cement. The aerosol Cement Finish transforms any object to look as if it is made of cement. Cement Finish is for indoor use only. Not intended for cement or concrete surfaces.

PRODUCT

| SKU | DESCRIPTION (Aerosol) |
|--------|-----------------------|
| 346338 | Cement Finish |

PRODUCT APPLICATION

Use outdoors or in a well ventilated area. Use when temperature is between 10-32°C (50-90°F) and humidity is below 65% to ensure proper drying. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

PRIMING

Priming is not required for most surfaces. For superior coverage, a Rust-Oleum® primer can be used for surfaces such as bare wood and treated wood.

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Hold can upright 25-30cm from surface and spray in a steady back and forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 21°C (70°F) and 50% relative humidity. Allow more time at cooler temperatures. May recoat within 1 hour or after 48 hours. Dries to the touch in 30 minutes.

NOTE: On plastic, maximum paint adhesion and durability is achieved in 5-7 days.

CLEAN-UP

Clean valve immediately after use by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral turps. Do not insert any object into can valve opening.

| | | |
|---|--|---------------|
| | TECHNICAL DATA | SPC-76 |
|  | RUST-OLEUM® CEMENT FINISH | |

PHYSICAL PROPERTIES

| | | CEMENT FINISH |
|--|------------------|-------------------------------------|
| Resin Type | | Alkyd |
| Pigment Type | | Titanium Dioxide, Aluminum |
| Solvents | | Acetone, Naptha, Xylene |
| MIR | | 0.80 Max |
| Fill Weight | | 340g |
| Practical Coverage (assumes 15% material loss) | | 0.74-0.92 m ² /can |
| Dry Times at 25°C and 50% Relative Humidity | Touch | 30 minutes |
| | Recoat | Within 1 hour or after 48 hours |
| | Handle | 2 hours |
| | Full Cure | 7 days |
| Shelf Life | | 12 months |
| Safety Information | | For additional information, see SDS |

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.