



# RUST-OLEUM® CHALKBOARD SPRAY

## DESCRIPTION AND USES

Rust-Oleum® Specialty Chalkboard Spray is a finish that converts wood, metal, plastic, glass, paperboard, and hardboard into a useable chalkboard surface.

## PRODUCT

SKU	DESCRIPTION (Aerosol)
-----	-----------------------

348762	Black
--------	-------

## PRODUCT APPLICATION

### READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

#### SURFACE PREPARATION

**ALL SURFACES:** Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Mold and mildew must be cleaned with a chlorinated cleaner or bleach solution. Rinse with fresh water and allow to thoroughly dry.

**STEEL:** Scrape and wire brush or power tool clean to remove loose rust, scale, and deteriorated coatings. Use Rust-Oleum Red Primer for sound rusted or clean metal before application of a finish coat.

**PREVIOUSLY COATED:** Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy surfaces should be scarified by sanding to create a surface profile.

## PRODUCT APPLICATION (cont.)

### APPLICATION

Apply only when air and surface temperatures are between 10-32°C and the relative humidity is below 85% to ensure proper drying. Use in a properly ventilated area. Cover surrounding area to protect from overspray. Overspray can carry a significant distance. Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE CAN**. Contact Rust-Oleum. Hold can upright 30-40 cm from surface and spray in a steady back and forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply several light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

When fully dry, prepare the surface for use by rubbing side of chalk over the entire surface. Erase and the chalkboard is ready for use. For best results, use only calcium carbonate chalk and felt erasers. Other chalks will scratch the surface.

### DRY & RECOAT

Dry and recoat times are based on 21°C and 50% relative humidity. Dries tack free in 20 minutes and can be handled in 1 hour. Recoat within 1 hour or after 24 hours.

### CLEAN-UP

Clean valve immediately after use by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean up wet paint with xylene or mineral turps. Throw away empty can in trash pick-up. Do not burn or place in home trash compactor.

### CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral turps. Do not insert any object into can valve opening.

	<b>TECHNICAL DATA</b>	<b>SPC-83</b>
<b>RUST-OLEUM® CHALKBOARD SPRAY</b>		

**PHYSICAL PROPERTIES**

		CHALKBOARD SPRAY
<b>Resin Type</b>		Acrylic Modified Alkyd
<b>Pigment Type</b>		Carbon Black
<b>Solvents</b>		Acetone, Butyl Acetate, Mineral Spirits, VM&P Naphtha, Xylene
<b>MIR</b>		0.80 Max
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		0.63 m <sup>2</sup> /can
<b>Dry Times at 21-27°C and 50% Relative Humidity</b>	<b>Tack Free</b>	20 minutes
	<b>Handle</b>	1 hour
	<b>Recoat</b>	Within 1 hour or after 24 hours
<b>Dry Heat Resistance</b>		93°C
<b>Shelf Life</b>		5 years
<b>Flash Point</b>		-104°C
<b>Safety Information</b>		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.